



上海世秀化工有限公司

Shanghai Seashow Chemical Co., Ltd.

[paulxuchen@126.com](mailto:paulxuchen@126.com) 徐晨 13735586926

## 产品说明书

### 水性脂肪族烫金胶：SX-606 SX-612 SX-630

#### 一、特征描述：

1. 本产品为水性脂肪族烫金胶。
- 2 本品转移涂层后，革面光泽自然、手感干滑、肉感强、附着力佳，耐水揉。

#### 二、使用说明：

使用于 PU 革等；适应三版机处理。一般使用 80 目或 100 目数轮处理等。使用中材料量应控制适当以保证表面稳定。

使用前请搅拌均匀，小试；

#### 三、技术指标：

外观： 半透明液体

成分： 脂肪族水性聚氨酯

溶剂： 软水

固含量： 30±2 %

粘度： SX-606 :600 CPS/25℃

SX-612:1200 CPS/25℃

SX-630:3000 CPS/25℃

包装： 180Kg 铁桶包装或根据客户要求包装。

#### 四、贮藏： 存放于阴凉干燥处，使用后请密封好，避免阳光直射；安全保质期为三个月。

备注：因各厂家生产工艺不同，故此工艺仅作参考。

# Product Instruction Booklet

## Waterborne Aliphatic Gilding Adhesive Resin: SX-606 SX-612 SX-630

### Feature Description:

This product is an aqueous aliphatic bronzing adhesive, after the transfer coating, the leather surface has natural luster, dry and smooth feel, strong flesh feeling, good adhesion and water resistance.

### Instructions:

It is suitable for PU leather, etc. Generally, 80 mesh or 100 mesh wheel processing is used. The amount of materials in use shall be controlled properly to ensure the surface stability.

Please mix well before use, and make a trial test for priority.

### Technical Indicators:

Appearance:	Translucent liquid
Ingredients:	Aliphatic Waterborne Polyurethane
Solvent:	Soft water
Solid content:	30 ± 2%
Viscosity:	SX-606: 600 CPS / 25 °C
	SX-612:1200 CPS/25°C
	SX-630:3000 CPS/25°C
Packaging:	180kg iron drum or according to customer requirements.

### Storage:

Store in a cool and dry place, please seal well after use, avoid direct sunlight; the safe shelf life is three months.

**Note: due to different production processes of different manufacturers, this process is only for reference.**